

CLAIMS:

52  
a 150  
1. Polypropylene having improved long chain branching and increased melt strength characterized in that it is produced by irradiating polypropylene with an electron beam having an energy of at least 5 MeV with a radiation dose of from 5 to 100 kGray in the presence of a grafting agent.

2. A polypropylene according to claim 1 wherein the electron beam energy to be used is of at least 10 MeV.

3. A polypropylene according to claim 1 or 2 wherein the grafting agent is selected from the group consisting of bismaleimide derivatives; mono-, di-, tri-, tetra-acrylate or methacrylate compounds; organosilane compounds of the formula  $A_4 \cdot nSiR_n$  where A are identical or different acrylate or methacrylate or vinyl groups, where R are identical or different alkoxy or acetoxy groups and where n is 1, 2, 3 or 4;  $\alpha, \beta$ -unsaturated acids and their anhydride derivatives; non-conjugated dienes such as 1,5-hexadiene, norbornadiene and dicyclopentadiene; dipentene; polybutadiene and copolymers containing polybutadiene blocks; butadiene based polymers and copolymers; polyisoprene and copolymers containing polyisoprene blocks; isoprene based polymers and copolymers; polyethylene;  $C_{4-20}$   $\alpha$ -olefins either linear or branched; styrene or divinylbenzene; ethylene-propylene rubbers and ethylene-propylene-diene rubbers; di-furnane derivatives; ester derivatives of fatty acids; and vinylpolybutadiene.

4. A polypropylene according to any one of claims 1 to 3 wherein the grafting agent comprises from 0.01 to 5 wt% of the weight of the polypropylene.

5. A polypropylene according to any one of claims 1 to 4 wherein the grafting agent comprises tetravinyl silane.

6. A polypropylene according to claim 5 wherein the tetravinyl silane is in an amount of from 0.01 to 1 wt% based on the weight of the polypropylene.

7. Polypropylene having a branching index of lower than 0.7 and an improved melt strength obtained by irradiating a polypropylene with an electron beam energy of at least 5 MeV with a radiation dose of 5 to 100 kGray in the presence of a grafting agent.

8. A process to produce a polypropylene with improved long chain branching and high melt strength in accordance with anyone of the preceding claims.

卷之三